CIVIL PRO

AN ISO 9001 : 2008 COMPANY & ACCREDITED LABORATORY AS PER ISO/IEC 17025:2017

4, 7TH MAIN MALLESWARAM, BANGALORE -3

Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID	:	**CP-2022-10-13-06**	**Date: 23/05/2022**
Customer	:	Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.	
Address	:	Project Sub Division, BBMP, Bangalore.	
Project Name	:	Providing RO Plant in Byatarayanapura in Ward No.07	
Agency	:	Sri.M C Adarsh, #2/427, 8th Main, 17th Cross, Agrahara Dasarahalli, Basaveshwaranagara, Bangalore-79	
Customer's Reference	:	EE(Project)/YnkZone/WO/135/2020-21	
Source of Sample	:	Sample supplied by Agency	
Sample Condition	:	Satisfactory	
Date of Receipt	:	18-05-22	
Customer ID	:	Column Concrete	
Sample Type /Size	:	150X150X150 mm	
Sample grade/Age	:	M25 / 7 Days Compressive Strength	
Reference to BIS codes	:	IS: 516 - 1959 (RA 2018) Methods of Tests for Strength of Concrete Cl.5	
Date of test	:	23/05/2022	

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Column Concrete	M25	16/05/2022	23/05/2022	151.25 X 149.24 X 149.33	22574	8.143	520.1	23.0	22.5
2	Column Concrete	M25	16/05/2022	23/05/2022	149.89 X 151.39 X 150.07	22692	8.251	505.3	22.3	
3	Column Concrete	M25	16/05/2022	23/05/2022	151.47 X 150.49 X 151.39	22794	8.628	508.1	22.3	

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.

All information furnished by Customer/Representative

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 30 days from the date of issue of test certificate

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL Pro BANGALORE Sig Date

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | ENVIRONMENTAL
WATER TESTING | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES

Scanned by TapScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY & ACCREDITED LABORATORY AS PER ISO/IEC 17025:2017
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2022-10-13-06**

Date: 15/06/2022

Customer : Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.

Address : Project Sub Division, BBMP, Bangalore.

Project Name : Providing RO Plant in Byatarayanapura in Ward No.07

Agency : Sri.M C Adarsh, #2/427, 8th Main, 17th Cross, Agrahara Dasarahalli, Basaveshwaranagara, Bangalore-79

Customer's Reference : EE(Project)/YnkZone/WO/135/2020-21

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 18-05-22

Customer ID : Column Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 (RA 2018) Methods of Tests for Strength of Concrete Cl.5

Date of test : 13/06/2022

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen	Cross sectional area	Weight of the sample	Failure Load	Compressive strength	Average Compressive Strength
					(mm)	(Sq.mm)	(kg)	(KN)	(N/mm^2)	(N/mm^2)
1	Column Concrete	M25	16/05/2022	13/06/2022	149.08 X 151.03 X 149.41	22515	8.355	624.2	27.7	27.4
2	Column Concrete	M25	16/05/2022	13/06/2022	151.47 X 151.17 X 151.26	22897	8.237	601.6	26.3	
3	Column Concrete	M25	16/05/2022	13/06/2022	149.27 X 150.86 X 149.23	22519	9.036	632.9	28.1	

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.

All information furnished by Customer/Representative

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 30 days from the date of issue of test certificate

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL Pro Sig Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Scanned by TapScanner

CIVIL PRO

AN ISO 9001 : 2008 COMPANY & ACCREDITED LABORATORY AS PER ISO/IEC 17025:2017

4, 7TH MAIN MALLESWARAM, BANGALORE -3

Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 30/05/2022

Lab ID	:	**CP-2022-10-13-06**
Customer	:	Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.
Address	:	Project Sub Division, BBMP, Bangalore.
Project Name	:	Providing RO Plant in Byatarayanapura in Ward No.07
Agency	:	Sri.M C Adarsh, #2/427, 8th Main, 17th Cross, Agrahara Dasarahalli, Basaveshwaranagara, Bangalore-79
Customer's Reference	:	EE(Project)/YnkZone/WO/135/2020-21
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	25-05-22
Customer ID	:	Lintel Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M25 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 (RA 2018) Methods of Tests for Strength of Concrete Cl.5
Date of test	:	30/05/2022

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Lintel Concrete	M25	23/05/2022	30/05/2022	150.77 X 150.62 X 151.95	22709	9.050	527.1	23.2	22.8
2	Lintel Concrete	M25	23/05/2022	30/05/2022	149.79 X 150.77 X 149.46	22584	8.843	506.8	22.4	
3	Lintel Concrete	M25	23/05/2022	30/05/2022	150.92 X 150.29 X 151.07	22682	8.214	517.1	22.8	

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.

All information furnished by Customer/Representative

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 30 days from the date of issue of test certificate

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL Pro
Sig.
Date
BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1

****End of Report****

Scanned by TapScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY & ACCREDITED LABORATORY AS PER ISO/IEC 17025:2017
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 21/06/2022

Lab ID	:	**CP-2022-10-13-06**
Customer	:	Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.
Address	:	Project Sub Division, BBMP, Bangalore.
Project Name	:	Providing RO Plant in Byatarayanapura in Ward No.07
Agency	:	Sri.M C Adarsh, #2/427, 8th Main, 17th Cross, Agrahara Dasarahalli, Basaveshwaranagara, Bangalore-79
Customer's Reference	:	EE(Project)/YnkZone/WO/135/2020-21
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	25-05-22
Customer ID	:	Lintel Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M25 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 (RA 2018) Methods of Tests for Strength of Concrete Cl.5
Date of test	:	20/06/2022

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Lintel Concrete	M25	23/05/2022	20/06/2022	149.83 X 151.39 X 149.92	22683	8.336	624.9	27.5	27.3
2	Lintel Concrete	M25	23/05/2022	20/06/2022	150.29 X 149.44 X 149.78	22459	8.702	588.4	26.2	
3	Lintel Concrete	M25	23/05/2022	20/06/2022	149.18 X 151.84 X 150.41	22652	8.654	637.9	28.2	

• The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL Pro BANGALORE Sig. Date

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | ENVIRONMENTAL
WATER TESTING | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES

Scanned by TapScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY & ACCREDITED LABORATORY AS PER ISO/IEC 17025:2017
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Certificate No.: TC-3548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 06/06/2022

Lab ID	:	CP-2022-10-13-06
Customer	:	Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.
Address	:	Project Sub Division, BBMP, Bangalore.
Project Name	:	Providing RO Plant in Byatarayanapura in Ward No.07
Agency	:	Sri.M C Adarsh, #2/427, 8th Main, 17th Cross, Agrahara Dasarahalli, Basaveshwaranagara, Bangalore-79
Customer's Reference	:	EE(Project)/Ynk/Zone/WO/135/2020-21
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	01-06-22
Customer ID	:	Roof Slab
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M25 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 (RA 2018) Methods of Tests for Strength of Concrete Cl.5
Date of test	:	06/06/2022

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Roof Slab	M25	30/05/2022	06/06/2022	150.02 X 149.49 X 149.02	22427	9.067	519.8	23.2	22.8
2	Roof Slab	M25	30/05/2022	06/06/2022	151.21 X 150.68 X 150.08	22784	8.959	514.2	22.6	
3	Roof Slab	M25	30/05/2022	06/06/2022	149.75 X 151.66 X 151.38	22712	8.812	511.4	22.5	

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.

All information furnished by Customer/Representative

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 30 days from the date of issue of test certificate

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL Pro BANGALORE Sig. Date

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | ENVIRONMENTAL
WATER TESTING | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES

Scanned by TapScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY & ACCREDITED LABORATORY AS PER ISO/IEC 17025:2017
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : CP-2022-10-13-06

Date: 27/06/2022

Customer : Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.

Address : Project Sub Division, BBMP, Bangalore.

Project Name : Providing RO Plant in Byatarayanapura in Ward No.07

Agency : Sri.M C Adarsh, #2/427, 8th Main, 17th Cross, Agrahara Dasarahalli, Basaveshwaranagara, Bangalore-79

Customer's Reference : EE(Project)/Ynk/Zone/WO/135/2020-21

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 01-06-22

Customer ID : Roof Slab

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 (RA 2018) Methods of Tests for Strength of Concrete CL5

Date of test : 27/06/2022

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen	Cross sectional area	Weight of the sample	Failure Load	Compressive strength	Average Compressive Strength
					(mm)	(Sq.mm)	(kg)	(KN)	(N/mm^2)	(N/mm^2)
1	Roof Slab	M25	30/05/2022	27/06/2022	149.54 X 150.81 X 150.89	22552	8.799	625.3	27.7	27.4
2	Roof Slab	M25	30/05/2022	27/06/2022	151.60 X 149.80 X 150.13	22709	8.707	591.8	26.1	
3	Roof Slab	M25	30/05/2022	27/06/2022	150.56 X 151.45 X 149.78	22802	8.739	649.8	28.5	

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.

All information furnished by Customer/Representative

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 30 days from the date of issue of test certificate

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Scanned by TapScanner